

**DESCRIPTION**

Recommended for metal surfaces that are exposed to very high temperatures +700°C. Contains only high-quality Silicone resin. Not suitable for surfaces in direct contact with fire.

PROPERTIES

- Viscosity: 18-25sec (Flow Cup DIN4, 20°C)
- Density: 0.6-0.8 g/L (Density Cup 100cm³/20°C, ASTM D – 1475)
- VOC content: 690 g/L
- Flash Point: -104°C (based on propellant)
- Drying time
 - Touch (20°C, Humidity<65%): 5-10min
 - Through dry (20°C, Humidity <65%): 1h
 - Maximum hardness: 24h
- Coverage: 5m²/L
- Gloss (GLOSS METER 60°ASTM D – 1471):
 - 0-4 GLOSS UNITS/MATT
- Contents: 400ml

INSTRUCTIONS FOR USE**APPLICATION**

The surface should be dry, clean, and at room temperature. Before use, shake the container for at least 2 minutes. Spray from a distance of 15-20cm and apply the paint in thin layers to achieve the necessary finish. Allow the product to dry for 24 hours and then heat the painted surface to 250°C for 30 minutes to achieve the optimal product properties. White fumes during the initial heating are normal.

Best application temperature: 10-25°C.

AFTER USE

Spray holding the can inverted for 3". Clean the caps with solvent.

STORAGE

Store between 5-35°C. Do not put in vehicles.

CAP SYSTEM**SMART CAP**

- Less overspray
- Extreme Coverage
- Fast drying
- Hard chisel lines
- Even coating
- Suitably for effects
- Dual way spraying

SAFETY

Request SDS

*Cap indicates the color of the paint

COLOR RANGE


350 SILVER



351 BLACK



352 WHITE



353 RED OXIDE



356 ANTHRACITE

